

MEASUREMENT RESULTS

THE NUMBERS ARE THERE! NO NEED TO THINK TWICE!

PARAMETER	STANDARD	UNIT	VALUE
Tensile Strength	ISO 527	MPa	39
Elastic-module – tensile	ISO 527	MPa	5246
Tensile Strain	ISO 527	MPa	1,81
Bending Strength	ISO 178	MPa	157
Elastic-module – bending	ISO 178	MPa	7030
Bending Strain	ISO 178	%	4,87
Izod impact resistance	ISO 180	kJ/m ²	55
Lol-limit oxygen index	ISO 4586	%	26
Barkol	ASTM D-2583 Co		48